

CLEAN VERSION OF AMENDMENTS

IN THE SPECIFICATION

Please amend the specification as follows.

Page 1, after the title, insert This is a divisional of application Serial No.

09/555,598, which is the National Stage of international application PCT/EP98/07784
filed December 1, 1998.--

IN THE CLAIMS

Please cancel claims 1-11.


Please add claims 12-25 as follows.

12. (new) A method of thermally or acoustically insulating a building, said method comprising installing a mat-form insulating material in the building, wherein the insulating material comprises at least one modified melamine resin fiber, which is obtained by condensing a melamine containing mixture with formaldehyde or a formaldehyde-supplying compound in a molar ratio of melamine to formaldehyde within the range from 1:1.15 to 1:4.5, said melamine mixture comprising

(A) from 90 to 99.9 mol% of a mixture comprising

(a) from 30 to 99.9 mol% of melamine and

(b) from 1.0 to 70 mol% of a substituted melamine of the general formula I



A²

where X^1 , X^2 and X^3 are each selected from $-NH_2$, $-NHR^1$ and $-NR^1R^2$, subject to the proviso that X^1 , X^2 and X^3 are not all $-NH_2$, and R^1 and R^2 are independently selected from hydroxy- C_2 - C_{20} -alkyl, hydroxy- C_2 - C_4 -alkyl-(oxa- C_2 - C_4 -alkyl)_n, where n is 1 to 5, and amino- C_2 - C_{12} -alkyl, or mixtures of melamines of formula I, and (B) from 0.1 to 10 mol%, based on (A) and (B), of a compound selected from phenols which are unsubstituted or substituted by radicals selected from C_1 - C_9 -alkyl and hydroxyl, C_1 - C_4 -alkanes substituted by two or three phenol groups, di(hydroxyphenyl) sulfones or mixtures thereof, wherein the insulating material has a density of from 10 to 150 g/l³.

13. (new) The method of claim 12, wherein the insulating material further comprises at least one polyalkylene terephthalate fiber.

14. (new) The method of claim 13, wherein the mat-form insulating material comprises

- a) from 5 to 95 % by weight of the melamine resin fiber, and
- b) from 5 to 95 % by weight of the polyalkylene terephthalate fiber.

15. (new) The method of claim 14, wherein the mat-form insulating material further comprises

- c) up to 30% by weight of further fibers and/or
- d) up to 20% by weight of additives.

16. (new) The method of claim 14, wherein the polyalkylene terephthalate fiber

is selected from polyethylene terephthalate fibers, polybutylene terephthalate fibers or mixtures thereof.

17. (new) The method of claim 16, wherein the polyethylene terephthalate fibers are bicomponent fibers having a core/sheath construction comprising a polyester core and a copolyester sheath.

18. (new) The method of claim 17, wherein the melting temperature of the core of the bicomponent fibers is within the range from 200 to 300°C, and the melting temperature of the sheath is within the range of from 80 to 150°C.

19. (new) The method of claim 17, wherein the individual fiber linear density of the bicomponent fibers is within the range of from 1 to 20 dtex.

20. (new) The method of claim 14, further comprising producing the mat-form insulating material by

mixing the melamine resin fiber and the polyalkylene terephthalate fiber to form a mixture,

laying down the mixture to form a mat, and

heating the mat.

21. (new) The method of claim 20, wherein the polyalkylene fiber is a bicomponent fiber having a core/sheath construction comprising a polyester core and a copolyester sheath and wherein the temperature of the heating is higher than the melting temperature of the sheath and lower than the melting temperature of the core.

22. (new) The method of claim 18, wherein the melting temperature of the core of the bicomponent fibers is within the range of from 230 to 280°C.

23. (new) The method of claim 18, wherein the melting temperature of the sheath of the bicomponent fibers is within the range of from 100 to 130°C.

24. (new) The method of claim 17, wherein the individual fiber linear density of the bicomponent fibers is within the range of from 2 to 15 dtex.

25. (new) The method of claim 12, wherein the insulating material has a density of from 15 to 50 g/l¹.

add B' >